



How to Use

KAMPEL FloorFil®



Seam Repair

FloorFil, custom color matched to your flooring, makes filling and repairing open seams as easy as 1-2-3!



Edge Damage

Accidental damage during installation can easily be repaired with FloorFil, after the flooring panel is installed.



Tool Damage

Surface damage caused by tools or any heavy, sharp objects accidentally dropped on the floor can easily be repaired with FloorFil.

Damage to older existing HPL flooring surfaces can be repaired using the procedure and application as specified in "Directions for Use."

Directions for Use

1. Use FF-99 Solvent to clean the flooring surface and damaged area or seam. FF-99 Solvent is the only recommended solvent to use with FloorFil.
2. Squeeze FloorFil onto a scrap piece of HPL flooring or cardboard. Using a KampeL hand polished putty knife, spread and work the FloorFil until it begins to thicken. Press the FloorFil into the damaged area or open seam.
3. Remove excess FloorFil using a cloth or a paper towel moistened with FF-99 Solvent.

FloorFil will begin to cure immediately. Drying time for normal floor traffic is approximately 1-2 hours. FloorFil will cure completely in approximately 6-8 hours. Second applications, if needed, can be applied within 1-2 hours. NOTE: FloorFil will shrink due to the solvents evaporating from the product. Larger seams and damaged areas may require a second application.

DISTRIBUTED BY:

Helpful Hints / Do's & Dont's

1. **DO** clean area to be repaired with FF-99 Solvent.
 2. **DO** use a KampeL hand polished putty knife when working with FloorFil and the flooring surface to prevent scratches.
 3. **DO** make certain the cap is replaced on the open tube and is properly sealed. FloorFil will cure in the tube if the cap is not replaced sealing the end of the tube.
 4. **DO REMEMBER** FloorFil is completely compatible with all melamine High Pressure Laminate flooring surfaces.
-
1. **DON'T** apply FloorFil directly from the tube. Excess shrinkage will occur.
 2. **DON'T** use any other petroleum distillate solvent with FloorFil. Excessive shrinkage and crazing may occur.
 3. **DON'T** use FF-99 Solvent on any other surfaces. FF-99 solvent will damage surface finishes such as enameled surfaces, acrylic enameled surfaces, stained wood surfaces, etc.
 4. **DON'T FORGET** FloorFil can be color matched by KampeL to any High Pressure Laminate Floor color or pattern.